



**Boral Construction Materials
Materials Technical Services**

Unit 4, 3-5 Gibbon Road
Baulkham Hills NSW 2153 Australia
PO Box 400, Winston Hills NSW 2153

T: +61 (02) 9624 9900
F: +61 (02) 9624 9999

www.boral.com.au

TEST REPORT

CLIENT: PERMA PRODUCTS

FILE No: 482/14

PROJECT: Quality Control

REQUEST No: 59312

SAMPLE DESCRIPTION: Rubber Tac Traction Tread Strips

DATE RECEIVED: 26.9.14

DATE OF TEST: 29.9.14

ENVIRONMENTAL CONDITIONS: Air Condition Room

TYPE OF RUBBER USED: 4S

TYPE OF CLEANING: Water only

NAME OF TESTING OFFICER: W. Komsta

TEST CONDUCTED: In Laboratory

TYPE OF TEST: Unfixed Surface

AIR TEMPERATURE AT TIME OF TEST: 23°C

**TEST PROCEDURE: AS/ 4586:2013 Appendix A – Wet Pendulum Test Method
For New Pedestrian Surface Materials**


Laboratory Sample No: 158669

TEST METHOD	TEST	RESULT
AS/ 4586, App. A	Wet Pendulum Test	
	The Mean British Pendulum Number For Each Test Specimen:	1. 36
	The Mean British Pendulum Number For the Sample:	36
	Classification achieved in accordance with AS/ 4586, Table 2.	P3

Note: Client had sent only one sample for testing
Sample submitted by client.
L. Back, File

W. KOMSTA



Approved Signatory 
Date 30.9.14 Serial No. 129570

NATA Accredited Laboratory